



## TVM Bull Seal

### Product Description:

TVM's Bull Seal is a revolutionary sealing product that will cure to form a bull strength seal even when applied on wet surfaces. This "one tube seals all" product will adhere to a wide range of building materials thus, eliminating the need for multiple sealants for a single project.

### Colors and Packaging:

Color	White
Part No. (US)	1-41-12-001
Part No. (CAN)	5-41-12-001

### Features:

- High bond strength and fast cure
- Color stable and UV resistant
- Paintable
- Water and mildew resistant
- Elastic rubber accommodates up to 20% movement

### Applications:

- Sealing and bonding
- Structural bonding in vibrating constructions

### Application Notes:

- Applications surfaces must be clean, free from foreign particles
- Porous surfaces must be primed

### Joint Dimension:

*Minimum Width:* 2 mm (bonding), 5 mm (joints)  
*Maximum Width:* 10 mm (bonding), 30 mm (joints)  
*Minimum Depth:* 5 mm (joints)  
*Recommendation:* width = 2 × depth

### Shelf Life:

12 months in unopened packaging when stored in a cool, dry place with temperatures between 41°F and 77°F (5°C and 25°C).

### Health and Safety Recommendations:

- Apply standard industrial hygiene
  - In case of emergency, contact INFOTRAC at 1.800.535.5053
- Please consult product label and MSDS for additional safety information.*

### Remarks:

- Paint compatibility test is recommended due to the wide range of paints available
- Due to the wide range of building substrates available, a preliminary compatibility test is recommended
- This product cannot be used as a glazing sealant
- Not suitable for use on polyethylene (PE), polypropylene (PP), and polytetrafluoroethylene (PTFE/Teflon®)

TDS -0141-08



#### CUSTOMER SERVICE and SALES

US 169 Jari Drive, Johnstown, PA 15904 CANADA 13383 Fourth Line, Acton ON

Phone: 1.866.484.4TVM (4886)

Fax: 1.877.SEND.TVM (736.3886)

Email: customerservice@tvmi.com

Technical Support: 1.888.TECH.TVM (832.4886)





# TECHNICAL DATA SHEET

www.tvmi.com

## TVM Bull Seal

### Physical Properties:

Base	Silylated Polymer
Consistency	Paste
Curing System	Moisture Cure
Skin Formation (20°C/65% R.H.)	5 minutes
Curing Rate (20°C/65% R.H.)	0.18 in/24 hours (3 mm/24 hours)
Cure Time (20°C/65% R.H.)	24 hours based on 1/4" bead
Hardness	50 ± 5 Shore A
Specific Gravity	1.47
Application Temperature	41°F to 95°F (5°C to 35°C)
Temperature Resistance	-40°F to 194°F (-40°C to 90°C)
Staining	Passes with no visible staining
Artificial Weathering (3000 hours in Xenon Arc)	Passes
Elastic Recovery	> 75%
Elongation at Break	500%
Adhesion in Peel	55 – 85 lb/in (981 – 1516 kg/m)
Elastic Modulus 100%	232 psi (1600 kPa)
Tear Strength	435 psi (3000 kPa)
Maximum Deformation	± 20%

### Shipping Information:

Size	Units/ Case	Case Weight	Dimensions (L" × W" × H")		Cases/ Pallet	Pallet Weight
			Case	Pallet		
9.8 fl.oz.	12	14 lbs	8 × 6.5 × 9.5	48 × 40 × 38	144	2016 lbs

TDS -0141-08



#### CUSTOMER SERVICE and SALES

US 169 Jari Drive, Johnstown, PA 15904 CANADA 13383 Fourth Line, Acton ON

Phone: 1.866.484.4TVM (4886)

Fax: 1.877.SEND.TVM (736.3886)

Email: customerservice@tvmi.com

Technical Support: 1.888.TECH.TVM (832.4886)

